



TECHNICAL CHARACTERISTICS

Technical property	Method	Result
SAE viscosity grade	SAE J300	5W-20
Density at 15°C	ASTM D-4052	0,8515
Flash point, °C	ASTM D-92	214
TBN (mg KOH/g)	ASTM D-2896	6,80
Pour point, °C	ASTM D-97	-39
Colour	ASTM D-1500	2,5
Viscosity index	ASTM D-2270	160
Kinematic viscosity at 40°C (cSt)	ASTM D-445	45,80
Kinematic viscosity at 100°C (cSt)	ASTM D-445	8,49

AKINAWA SN/CF 5W-20 100% Synthetic

SN/CF 5W-20 100% Synthetic is a fully synthetic resource conserving motor oil and meets the GF-5 standard for engine oils, set by the International Lubricants Standardization and Approval Committee (ILSAC). The newest ZDDP anti-wear additive package delivers the latest development in lubricating technology to maximize protection and cleanliness for the newest gasoline-fuelled engines.

APPLICATION

SN/CF 5W-40 100% Synthetic meets the requirements of gasoline and light diesel engines that confirm to modern environmental standards and are equipped with direct injection systems, variable valve timing, with and without turbocharging. The product provides engine protection under extended heavy load conditions. The operational and environmental performance of the product meets API, ACEA, MERCEDES-BENZ and PORSCHE standards. Recommended for all-season use.

SPECIFICATIONS / APPROVALS

- Api SN/CF · ILSAC GF-5 · Dexos1·Toyota00279-5W20-01 · Honda08798-9027 · Nissan 999PK-5W20W5
- Subaru SOA868V9280 · Mazda 0000-77-5W20-QT ·BMW 83 21 2 365 954 ·Mercedes-Benz000989890110
- AudiG 052 167 M4 ·Volkswagen G 052 167 M4 ·Hyundai 05100-00451 ·KiaUM020-CH031
- Volvo 31439822 ·Peugeot9736.A6 · Renault 7711578156 ·Fiat 9.55535-GSX ·Ford XO-5W20-5QSP
- Chevrolet 88865636 ·Jeep68218891AA

APPLICATION BENEFITS

- SN/CF 5W-20 100% Synthetic provides:
- Ease of use in both gasoline and diesel engines
 - Excellent detergency due to high base number
 - Low oil consumption through burning
 - Extended drain interval
 - Reliable engine protection against wear
 - Stable performance in all-season use

The above information is based on data of which we are aware and is believed to be correct as of the date hereof. Since the information contained herein may be applied under conditions beyond our control and with which we may be unfamiliar and since data made available subsequent to the date hereof may suggest modifications of the information, we do not assume any responsibility for the results of its use. This information is furnished upon the condition that the person receiving it shall make his own determination of the suitability of the material for his particular purpose. Therefore, no warranty either express or implied of merchantability or fitness for particular purpose is made with respect to the product or the information contained herein.